

Bravo is a full aniline waxed pull-up leather. Slight distressed, Bravo with a unique two-tone effect and an exclusive waxy top coat that makes it very elegant.

## Details

Thickness	0,9-1,1 mm
Leather type	Aniline
Raw material	European
Tannage	Chrome tannage
Dyeing	Dyed-Through Aniline
Finishing	Waxed Aniline

## Technical Characteristics \*

Property	Performance	Test Method
Dry rub fastness	50 cycles val. $\geq 4$ Grey Scale	UNI EN ISO 11644
Wet rub fastness	20 cycles val. $\geq 3/4$ Grey Scale	UNI EN ISO 11640
Alcaline perspiration rub fastness	10 cycles val. $\geq 3$ Grey Scale	UNI EN ISO 11640

## Physical Characteristics \*

Property	Performance	Test Method
Adhesion of finishing	not applicable	UNI EN ISO 11644
Tear resistance	$\geq 20$ N	UNI EN ISO 3377-1
Flex resistance	not applicable	UNI EN ISO 5402
Flammability resistance	Pass	TB117-2013

## Chemicals Characteristics \*

Property	Performance	Test Method
pH determination and difference figure ( $\Delta$ pH)	$\text{pH} \geq 3,2 / \Delta \text{pH} \leq 0,7$	UNI EN ISO 4045
Azo-dyes (Directive 2002/61/CE)	Absents ( $< 30$ ppm)	UNI CEN ISO/TS 17234
Pentachlorophenol content	$< 5$ ppm	UNI EN ISO 17070
Exavalent Chromium content	$< 3$ ppm	UNI EN ISO 17075
Formaldehyde content	$< 75$ ppm	UNI CEN ISO/TS 17226
Lead content in finish	$\leq 90$ ppm	CPSC-CH-E 1003-09.1
Cadmium content finish	$\leq 75$ ppm	CPSC-CH-E 1003-09.1

\* Tests are performed on intact leather not manipulated.

**Our leather standards comply with requirements of REACH Regulation.**

## Cleaning and Maintenance

Remove with a soft and dry cloth for regular cleaning.

Don't rub and never use abrasive or aggressive products like solvents, stain removers, etc.

We recommend to avoid the exposure to direct sun and direct heat.

**Conceria TRUST s.r.l.** Via Strada dei Laghi 14 - 36072 Chiampo (VI) - ITALY

Tel. +39 0444 624052 - Fax. +39 0444 422822

[www.conceriatrust.it](http://www.conceriatrust.it)