

Seta is a natural grain bovine leather. This leather's name says it all: the rich oil infusion creates a light pull up effect and a very smooth and soft hand. Seta has a smooth feel similar to the texture of Nubuck, fantastically soft to the touch.

Details

| | |
|--------------|----------------------|
| Thickness | 0,9-1,1 mm |
| Leather type | Aniline |
| Raw material | Brazilian TRI |
| Tannage | Chrome tannage |
| Dyeing | Dyed-Through Aniline |
| Finishing | Oiled - Aniline |

Technical Characteristics *

| Property | Performance | Test Method |
|------------------------------------|--------------------------------------|------------------|
| Dry rub fastness | 50 cycles val. ≥ 4 Grey Scale | UNI EN ISO 11640 |
| Wet rub fastness | 20 cycles val. $\geq 3/4$ Grey Scale | UNI EN ISO 11640 |
| Alcaline perspiration rub fastness | 10 cycles val. $\geq 2/3$ Grey Scale | UNI EN ISO 11640 |

Physical Characteristics *

| Property | Performance | Test Method |
|-------------------------|----------------|-------------------|
| Adhesion of finishing | not applicable | UNI EN ISO 11644 |
| Tear resistance | ≥ 20 N | UNI EN ISO 3377-1 |
| Flex resistance | not applicable | UNI EN ISO 5402 |
| Flammability resistance | Pass | TBI 17-2013 |

Chemicals Characteristics *

| Property | Performance | Test Method |
|---|--|----------------------|
| pH determination and difference figure (Δ pH) | $\text{pH} \geq 3,2 / \Delta \text{pH} \leq 0,7$ | UNI EN ISO 4045 |
| Azo-dyes (Directive 2002/61/CE) | Absents (< 30 ppm) | UNI CEN ISO/TS 17234 |
| Pentachlorophenol content | < 5 ppm | UNI EN ISO 17070 |
| Exavalent Chromium content | < 3 ppm | UNI EN ISO 17075 |
| Formaldehyde content | < 75 ppm | UNI CEN ISO/TS 17226 |
| Lead content in finish | ≤ 90 ppm | CPSC-CH-E 1003-09.1 |
| Cadmium content finish | ≤ 75 ppm | CPSC-CH-E 1003-09.1 |

* Tests are performed on intact leather not manipulated.

Our leather standards comply with requirements of REACH Regulation.

Cleaning and Maintenance

Remove with a soft and dry cloth for regular cleaning.

Don't rub and never use abrasive or aggressive products like solvents, stain removers, etc.

We recommend to avoid the exposure to direct sun and direct heat.

Conceria TRUST s.r.l. Via Strada dei Laghi 14 - 36072 Chiampo (VI) - ITALY

Tel. +39 0444 624052 - Fax. +39 0444 422822

www.conceriatrust.it