

Vermont is a natural grain bovine leather. Shiny leather inspired by Vermont combines classic looks with authentic trail markings. A soft hand feel and a richness top coat, give to this product an outstanding characters.

## Details

|              |                      |
|--------------|----------------------|
| Thickness    | 0,9-1,1 mm           |
| Leather type | Aniline              |
| Raw material | Brazilian TR1        |
| Tannage      | Chrome tannage       |
| Dyeing       | Dyed-Through Aniline |
| Finishing    | Waxed Aniline        |

## Technical Characteristics \*

| Property                           | Performance                          | Test Method      |
|------------------------------------|--------------------------------------|------------------|
| Dry rub fastness                   | 50 cycles val. $\geq 4$ Grey Scale   | UNI EN ISO 11644 |
| Wet rub fastness                   | 20 cycles val. $\geq 3/4$ Grey Scale | UNI EN ISO 11644 |
| Alcaline perspiration rub fastness | 10 cycles val. $\geq 3/4$ Grey Scale | UNI EN ISO 11640 |

## Physical Characteristics \*

| Property                | Performance     | Test Method       |
|-------------------------|-----------------|-------------------|
| Adhesion of finishing   | $\geq 2$ N/10mm | UNI EN ISO 11644  |
| Tear resistance         | $\geq 20$ N     | UNI EN ISO 3377-1 |
| Flex resistance         | not applicable  | UNI EN ISO 5402   |
| Flammability resistance | Pass            | TBI 17-2013       |

## Chemicals Characteristics \*

| Property  | Performance  | Test Method          |
|---|--|----------------------|
| pH determination and difference figure ( $\Delta$ pH) | $\text{pH} \geq 3,2$ / $\Delta \text{pH} \leq 0,7$ | UNI EN ISO 4045      |
| Azo-dyes (Directive 2002/61/CE)                       | Absents ( $< 30$ ppm)                              | UNI CEN ISO/TS 17234 |
| Pentachlorophenol content                             | $< 5$ ppm  | UNI EN ISO 17070     |
| Exavalent Chromium content                            | $< 3$ ppm  | UNI EN ISO 17075     |
| Formaldehyde content                                  | $< 75$ ppm   | UNI CEN ISO/TS 17226 |
| Lead content in finish                                | $\leq 90$ ppm                                      | CPSC-CH-E 1003-09.1  |
| Cadmium content finish                                | $\leq 75$ ppm                                      | CPSC-CH-E 1003-09.1  |

\* Tests are performed on intact leather not manipulated.

Our leather standards comply with requirements of REACH Regulation.

## Cleaning and Maintenance

Remove with a soft and dry cloth for regular cleaning.

Don't rub and never use abrasive or aggressive products like solvents, stain removers, etc.

We recommend to avoid the exposure to direct sun and direct heat.